



# Connex500™ Digital Material™ Data Sheets

## Cartridges: VeroWhite, TangoBlack

Primary material: VeroWhite Secondary material: TangoBlack

RIGID

Property	ASTM	Units	DM 8110	DM 8120	DM 8130
Tensile Strength	D-638-03	MPa	52	42	30
Modulus of Elasticity	D-638-03	MPa	2690	2400	1800
Elongation at Break	D-638-03	%	17	34	52
Flexural strength	D-790-03	MPa	77	65	42
Flexural modulus	D-790-03	MPa	2580	2190	1620
HDT at 0.45 MPa	D-648-06	°C	42	41	39
Notched Izod Impact	D-256	J/m	26	26	35

Primary material: TangoBlack Secondary material: VeroWhite

FLEXIBLE

Property	ASTM	Units	DM 9110	DM 9120	DM 9130
Tensile Strength	D-412	MPa	3	4	9
Elongation to break	D-412	%	50	40	39
Tensile tear resistance	D-624 De C	N/mm	8	15	47
Hardness shore A	D-2240		80	85	95

## Cartridges: FullCure720, TangoBlack

Primary material: FullCure720 Secondary material: TangoBlack

RIGID

Property	ASTM	Units	DM7210	DM 7220	DM 7230
Tensile Strength	D-638-03	MPa	56	54	47
Modulus of Elasticity	D-638-04	MPa	2300	2150	1750
Elongation at Break	D-638-05	%	15-25	15-25	15-25
Flexural strength	D-790-03	MPa	88	84	72
Flexural modulus	D-790-04	MPa	2500	2450	2350
HDT at 0.45 MPa	D-648-06	°C	50	49	46
Notched Izod Impact	D-256-06	J/m	24	24	24

Primary material: TangoBlack Secondary material: FullCure720

FLEXIBLE

Property	ASTM	Units	DM 9410	DM 9420	DM 9430
Tensile Strength	D-412	MPa	3	4	9
Elongation to break	D-412	%	50	40	39
Tensile tear resistance	D-624 De C	N/mm	8	15	47
Hardness shore A	D-2240		80	85	95

## Cartridges: VeroWhite, VeroBlack

Primary material: VeroWhite Secondary material: VeroBlack

RIGID

Property	ASTM	Units	DM8310	DM 8320	DM 8330
Tensile Strength	D-638-03	MPa	48	48	48
Modulus of Elasticity	D-638-03	MPa	2750	2750	2750
Elongation at Break	D-638-03	%	25	25	25
Flexural strength	D-790-03	MPa	78	78	78
Flexural modulus	D-790-03	MPa	2570	2570	2570
HDT at 0.45 MPa	D-648-06	°C	41	41	41
Notched Izod Impact	D-256	J/m	26	26	26

**Cartridges: VeroBlue, VeroBlack****Primary material:** VeroBlue **Secondary material:** VeroBlack

RIGID

Property	ASTM	Units	DM 8110
Tensile Strength	D-638-03	MPa	48
Modulus of Elasticity	D-638-03	MPa	2750
Elongation at Break	D-638-03	%	25
Flexural strength	D-790-03	MPa	78
Flexural modulus	D-790-03	MPa	2570
HDT at 0.45 MPa	D-648-06	°C	41
Notched Izod Impact	D-256	J/m	26

**Cartridges: DurusWhite, VeroBlack****Primary material:** DurusWhite**Secondary material:**  
VeroWhite VeroBlue VeroBlack FullCure720

RIGID

Property	ASTM	Units	DM 4310	DM 4410	DM4510	DM4710
Tensile Strength	D-638-03	MPa	33	33	33	33
Modulus of Elasticity	D-638-04	MPa	1400	1400	1400	1400
Elongation at Break	D-638-05	%	45	45	45	45
Flexural strength	D-790-03	MPa	43	43	43	43
Flexural modulus	D-790-04	MPa	1500	1500	1500	1500
HDT at 0.45 MPa	D-648-06	°C	43	43	43	43
Notched Izod Impact	D-256-06	J/m	42	42	42	42

**Cartridges: FullCure720, VeroBlack****Primary material:** FullCure720 **Secondary material:** VeroBlack

RIGID

Property	ASTM	Units	DM Dots 7513	DM Grid 7523
Tensile Strength	D-638-03	MPa	60.3	60.3
Modulus of Elasticity		MPa	2870	2870
Elongation at Break	D-638-05	%	20	20
Flexural strength	D-790-03	MPa	75.8	75.8
Flexural modulus	D-790-04	MPa	1718	1718
HDT at 0.45 MPa	D-648-06	°C	48.4	48.4
Notched Izod Impact	D-256	J/m	23.6	23.6

**Cartridges: TangoBlack, VeroBlue****Primary material:** TangoBlack **Secondary material:** VeroBlue

FLEXIBLE

Property	ASTM	Units	DM 9210	DM 9220	DM 9230
Tensile Strength	D-412	MPa	3	4	9
Elongation to break	D-412	%	50	40	39
Tensile tear resistance	D-624 De C	N/mm	8	15	47
Hardness shore A	D-2240		80	85	95

**Cartridges: TangoGray, TangoBlack****Primary material:** TangoGray **Secondary material:** TangoBlack

FLEXIBLE

Property	ASTM	Units	DM 9510
Tensile Strength	D-412	MPa	2
Elongation to break	D-412	%	37
Tensile tear resistance	D-624 De C	N/mm	6
Hardness shore A	D-2240		65

**Cartridges: TangoGray, VeroBlack****Primary material:** TangoGray **Secondary material:** VeroBlack

FLEXIBLE

Property	ASTM	Units	DM 9610
Tensile Strength	D-412	MPa	11
Elongation to break	D-412	%	49
Tensile tear resistance	D-624 De C	N/mm	47
Hardness shore A	D-2240		80

Objet Geometries Ltd.  
Headquarters  
2 Holtzman st.,  
Science Park,  
P.O Box 2496,  
Rehovot 76124, Israel  
T: +972-8-931-4314  
F: +972-8-931-4315

Objet Geometries Inc.  
North America  
5 Fortune Drive  
Billerica,  
MA 01821  
USA  
T: +1-877-489-9449  
F: +1-866-676-1533

Objet Geometries  
GmbH  
Im Leuschnerpark 4,  
64347 Griesheim  
Germany  
T: +49-6155-605-346  
F: +49-6155-605-344

Objet Geometries AP  
Asia Pacific  
Unit28, 10/f, HITEC  
1 Trademart Drive  
Kowloon Bay, Kowloon  
Hong Kong  
T: +852-217-40111  
F: +852-217-40555

Objet Geometries AP  
Limited China Rep Office  
Rm1220, CIMIC Tower,  
1090 Century Blvd,  
Pudong Shanghai  
2000120 P. R. China  
T: +86-21-5836-2468  
F: +86-21-5836-2469



info@objet.com www.objet.com

© 2009 Objet, Quadra, QuadraTempo, PolyJet, FullCure, SHR, Eden, Eden250, Eden260, Eden260V, Eden330, Eden350, Eden350V, Eden500V, Job Manager, Objet Studio, CADMatrix, Connex, Connex500, Alaris, Alaris30, PolyLog, TangoBlack, TangoGray, TangoPlus, VeroBlue, VeroWhite, VeroBlack, Durus, DigitalMaterials, PolyJetMatrix and ObjetGreen are trademarks of Objet Geometries Ltd. and may be registered in certain jurisdictions. All other trademarks belong to their respective owners.